

Strenx 900 MC

Advanced High Strength steel

General Product Description

Strenx 900 MC is a hot-rolled structural cold-forming steel with a minimum yield strength of 900 MPa. The steel meet and exceed the requirements of S900MC in EN 10149-2. Typical applications are advanced lifting devices and lighter transport solutions and components.

Available dimensions

Strenx 900 MC is available as cut to length sheets with mill edge in thicknesses of 3.00 - 10.00 mm, widths up to 1600 mm and lengths up to 13 meters.

Mechanical Properties

Yield strength R _{eH} ¹⁾ Min MPa	Tensile strength R _m MPa	Elongation A ₅ Min % Sheet thickness t ≥ 3mm
900	930 - 1200	8

The mechanical properties are tested in the longitudinal direction.

¹⁾ If R_{eH} is not applicable then R_{p0.2} is used.

Impact properties	900 MC -40°C
Minimum energy for test on longitudinal Charpy V 10x10 mm test specimens (J)	27

Impact testing according to EN 10149-2 (-20 °C /minimum 40J) is available if specified at the time of order.

Impact testing according to EN ISO 148-1 is performed on thicknesses ≥ 5mm. The specified minimum value corresponds to a full-size specimen.

Bending properties	3 mm ≤ t ≤ 8 mm	t > 8mm
Min. inner bending radius for a 90° bend	3.0xt	3.5xt

For both longitudinal and transverse direction.

Chemical Composition (ladle analysis)

C % Max	Si % Max	Mn % Max	P % Max	S % Max	Al _{tot} % Min	Nb % Max	V % Max	Ti % Max
0.10	0.25	1.30	0.020	0.010	0.015	0.05 ¹⁾	0.05 ¹⁾	0.07 ¹⁾

The steel is grain refined.

¹⁾ Sum of Nb, V and Ti is max 0.18%.

Carbon equivalent

	3 mm ≤ t < 8 mm	8 mm ≤ t ≤ 10 mm
CET / CEV Typical	0.25 / 0.50	0.27 / 0.53

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$$

Tolerances

More details are given on www.ssab.com.

Thickness

Tolerances according to Strenx Thickness Guarantees.
Strenx Guarantees offer considerably narrower thickness tolerances compared to EN 10 051.

Length and width

Width and length tolerances according to SSAB standard.
The SSAB standard offer narrower width and length tolerances compared to EN 10 051.
Length tolerances only apply for cut to length sheets.

Shape

Tolerances according to EN 10 051.
Narrower tolerances according to the SSAB standard are available on request.

Flatness

Tolerances according to Strenx Flatness Guarantees Class A.
Strenx Flatness Guarantees offer narrower tolerances compared to EN 10 051.
Flatness guarantees only apply for cut to length sheets.

Surface Properties

According to EN 10 163-2 Class A, Subclass 3.

Delivery Conditions

Strenx 900 MC is supplied in as rolled surface condition, pickled surface is available in a limited thickness range.
The product is thermomechanically rolled.

Fabrication and Other Recommendations

Strenx 900 MC has good welding, cold forming and cutting performance.

Strenx 900 MC is not suited for applications requiring hot working or heat treatments at temperatures above 400°C since the material then may lose its guaranteed properties.

For information concerning fabrication, see SSAB's brochures on www.ssab.com or consult Tech Support, techsupport@ssab.com.

Appropriate health and safety precautions must be taken when bending, welding, cutting, grinding or otherwise working on the product.

Contact and Information

For information, see SSAB's brochures on www.ssab.com or consult Tech Support, techsupport@ssab.com.